



PROPERTY	VALUE	ASTM
Melt Index, 190°C/2.16kg (g/10 min)	4.0	D 1238
Density (g/cm³)	0.923	D 1505
Ultimate Tensile (psi)	1600	D 638
Elongation (%)	450	D 638

Description

MARPOL® LDC 740 is a low density resin recommended for use in boardstock coating. This material has an excellent combination of low neck-in, ease of processing, and good chill-roll release.

Recommended Applications

Milk cartons, liquid containers, multiwall bag stock and frozen food containers

FDA

This product has some 21 CFR clearances

This information, to our knowledge, is believed to be correct. The use of this product in its actual conditions are beyond our control and satisfactory results for this product is the customer's sole responsibility.

