



MARPOL
Homo 3.0
Homopolymer Polypropylene



PRODUCT DATA SHEET

PROPERTY	VALUE	ASTM
Melt Index (230°C /2.16kg)	3.0	D 1238
Density - Specific Gravity (Method B)	0.902	D 792
Tensile Strength at Yield (psi)	5100	D 638
Flexural Modulus (psi)	222000	D 790
Tensile Elongation at Yield (%)	11	D 638
Izod Impact Notched @ 73 °F (ft.lb./in) @ 23 °C (J/m)	0.972 52	D 256

Additives: None

Recommended Applications: Stationery film, housewares, raffia//tapes/strapping, Also good for clear and opaque containers.

Homo 3.0 is a low flow polypropylene homopolymer resin available in pellet form. Homo 3.0 is often used in general injection molding or extrusion applications, and is most frequently sold into raffia markets.

This information, to our knowledge, is believed to be correct. The use of this product in its actual conditions are beyond our control and satisfactory results for this product is the customer's sole responsibility.